

DESCRIPTION

A one component, water based, highly vapor permeable primer designed to enhance adhesion of vapor permeable, self adhered air barrier membranes.

USES

For use with AirOutshield™ SA280 and other self-adhered membranes. Apply over substrates that are difficult to achieve adequate adhesion to without a primer.

PACKAGING

Product Code	Packaging	Weight
PRM01	1 Gallon US	4 kg (9 lb)
PRM05	5 Gallon US	20 kg (44 lb)

INSTALLATION

Surfaces must be dry, free from oil, grease, and other contaminants and particles.

Apply SRP HP Primer to the substrate by brush, roller, or airless sprayer. Application rates will vary from 250 to 400 sq ft per gallon. Can be applied when surface and ambient temperature is 5°C (41°F). For application at temperature below 5°C (41°F), consider using SRP AT Adhesive.

First apply to a small test area of the substrate to confirm adequate adhesion. Apply SRP HP Primer to the substrate area designated for the self-adhered sheet membrane, extending approximately 1 in. (25 mm) beyond the perimeter to ensure full edge adhesion. Apply the membrane as soon as the primer has fully cured to ensure maximum tack and optimal adhesion. Only prime surfaces that will receive the membrane within the same working day. Any areas left exposed for an extended period must be re-primed prior to installation. The estimated dry time is between 30 minutes to 2.5 hours, depending on several factors including: ambient air temperatures, humidity, air circulation and wind conditions.

COMPATIBILITY

Compatible with OSB, concrete, CMU (block), glass mat and paper faced gypsum board, XPS, EPS, Polyisocyanurates and other substrates.

PRECAUTIONS & LIMITATIONS

Do not allow the primer to freeze; any primer that has been frozen and thawed must be discarded. Store the primer in a dry, temperature-controlled location above 5 °C (41°F).

Do not over apply; maintain a rate of 250 to 400 sq ft per gallon. Remove overspray immediately.

TECHNICAL SERVICE

Contact us at info@SRPAirOut.com or 866 533 0233

Warranty: The information, and in particular, the recommendations relating to the application and end-use of SRP AirOutshield products, are given in good faith based on SRP AirOutshield's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Technical Data Sheet for the product concerned, copies of which will be supplied on request or can be accessed on the Internet at www.SRPAirOutshield.com.